

ChovASTAR FIBRATED WATERPROOFING

CHOVASTAR®

Red 20kg 75241 - 5kg 75212

Grey 20kg 75242

White 20kg 75243

Reinforced roof protection from dump and rain

Description

ChovASTAR® FIBRATED WATERPROOFING is a red dense acrylic based waterproofing product with added fibers to provide greater consistency.

It is recommended to apply as visitable terraces exterior finish as a protection against dump and rain. It can also be used as reinforcement of singular points.



Fiber reinforced
Excellent protection
Tough and resilient

5kg
20kg

Installation

Surface on apply must be dry, clean and free of dust, grease, solvents, etc. Ambient temperature should be above 5 °C and no likelihood of rain.

Remove the product perfectly. Apply a first layer by roller or brush. Let it dry 4-6 hours and apply a second additional layer. **The use of reinforcing mesh is not necessary.**



white

red

grey



In case of doubt about the installation, please contact our Technical Department.

 ChovA

Waterproofing solutions

Fibrated Waterproofing

ChovASTAR FIBRATED WATERPROOFING

CHOVASTAR®

Reinforced roof protection from dump and rain

Additional information

Presentation: Plastic container. Content 5 kg.

Performance: Depending on the surface, the approximate yield is 1 kg/m² per layer. With a pot, 2,5 m² are covered using two layers.

Cleaning: If product is fresh, tools used can be easily cleaned with water. Once dry, must clean using solvents.

Storage: Store it protected from weather, out of sun and temperatures above 5 °C.

Technical Specifications

DRYING TIME.....	4-6 hours
APPLICATION TEMPERATURE.....	5 °C to 30 °C
INFLAMMABILITY	NON-FLAMMABLE
COMBUSTIBILITY	NON-COMBUSTIBLE
DOES NOT CONTAIN SOLVENTS	
COLOR	RED, WHITE OR GREY

Fibrated Waterproofing

Provided information matches up with average own data. ChovA guarantee is limited to product quality. Regarding commissioning work, must meet specified installation requirements.



ChovA



Waterproofing solutions