

ChovATERM® XPS-40 POL PY 30

MODIFIED BITUMEN WITH ELASTOMER (SBS) SHEET

COMPLEX - **POLITABER**WITH THERMAL INSULATION (XPS)

TECHNICAL FILE Nº 35015 - REVIEW 8/13 THIS REVIEW CANCELLS ALL PREVIOUS

PRODUCT.-



ChovATERM® is a complex formed by a thermal insulation, with strips cut from XPS panels—**ChovAFOAM**, thermally adhered to bituminous sheets of modified with elastomers bitumen - **POLITABER**.

ChovATERM® is presented in rolls of dimensions 6 X 1 m (Length X Width) for 40mm insulation thickness. The insulation strips have 4 cm thickness and approximately 5 cm width. And its 92 cm long, is the corresponding to allow 8 cm free overlap.

Components characteristics are described in Technical files of the corresponding products, **ChovAFOAM** and **POLITABER**

THERMAL INSULATION.

Extruded polystyrene rigid foam plates with closed cell structure. Corresponds to **ChovAFOAM 300 M40** panel characteristics.

WATERPROOFING SHEET.

Elastomer modified bitumen, SBS sheet. Corresponds to POLITABER POL PY 30 sheets characteristics.

Notes.- The complex components products, insulation and related bituminous sheet, have the compulsory product CE trade and quality mark, AENOR, according to the respective UNE EN Standards. Although complex, consisting of two distinct components, cannot has CE trade, as it is not a "product" but a complex. Equivalently, also has not AENOR.

ChovATERM applying system is always by mechanical fastening. Fasteners types and application instructions are details in specific brochures. Request them for a correct implementation.

Insulation requirements and waterproofing sheets composition are made according to applicable regulations general requirements. To this end, it may use another insulation panels layer and / or sheets, if required by the specification, to meet DB and DB-HE-HS requirements.

Date: 15th, December 2013

Provided information matches up with data obtained in our own laboratories and/or accredited external laboratories. This product will maintain these characteristics on average. **ChovA, S. A.** reserves the right to modify or cancel any parameter without previous notice. **ChovA, S. A.** guarantee is limited to the product quality. As for commissioning work, which do not participate, the product installation instructions must be followed carefully. Soundproofing values may differ from those shown here due to improper execution of work. This technical file will be voided by subsequent revisions and, if in doubt, request the latest revision.



ChovATERM® XPS-40 POL PY 30

MODIFIED BITUMEN WITH ELASTOMER (SBS) SHEET COMPLEX - **POLITABER**WITH THERMAL INSULATION (XPS)

TECHNICAL FILE Nº 35015 - REVIEW 8/13 THIS REVIEW CANCELLS ALL PREVIOUS

COMPLETE INFORMATION OF ChovAFOAM 300 M40 INSULATING PANELS



View "Declaración de Prestaciones – **DoP**" in: DoP_E_81910A_13164_CHOVAFOAM300M40_v02 (And other references)

View CE Trade, complete, in: DoP_E_81910A_13164_CHOVAFOAM300M40_v02 (And other references)

ASFALTOS CHOVA, S.A.
Ctra. Tavernes a Liria, km 4,3. 46760 TAVERNES DE LA VALLDIGNA. Valencia

Panel description:

Extruded polystyrene rigid foam panel, XPS, closed cell structure, usable as thermal insulation.

Uses according: Standard EN 13164, "CEC" of CTE. (Constructive Elements Catalogue) and UNE 104401

Extruded polystyrene thermal insulating panel, XPS, 40 mm thick. The strips are obtained from this panel.

Recommended use: according ChovATERM system.

Do not use at temperatures higher than 65 °C.

STORAGE: with the original presentation and rolls protected from sun (UV rays).

CHARACTERISTIC	VALUE		UNIT	STANDARD		
Reaction to fire. Euroclasses characteristics	Clase E			EN 13501-1		
Combustion with continuous incandescence. (Test method under development. Value will be defined when applying the Standard)	NPD			PrEN xxx		
Water vapour permeability. Water vapour transmission	80		(µ)	EN 12086		
Thermal Resistance. Thermal Conductivity	Thickness mm	R_D		EN 12667 /		
$\lambda_D = 0.034 \text{ m K / W}, \text{ de } 40 \text{ mm}$	40	1,20	m ² K / W	12939		
Water permeability. Long-term water absorption	≤ 0,7		%	EN 12087		
Compression resistance. Compressive contraction in compression resistance	≥ 300		kPa	EN 826		
Traction / bending resistance. Traction resistance perpendicular to the faces	≥ 900		(om TR900)	EN 1607		
Reaction to fire durability regarding heat or weathering exposure, aging / degradation	NPD					
Thermal resistance durability regarding heat or weathering exposure, aging / degradation	NPD					
Compression resistance durability regarding aging/degradation	NPD					
CE DESIGNATION CODE EN 13164 -T1-DS(70,-) – DS (23,90) -DLT(2)5-CS(10/Y)300 - WL(T)0,7.)						



ChovATERM® XPS-40 POL PY 30

MODIFIED BITUMEN WITH ELASTOMER (SBS) SHEET COMPLEX - **POLITABER**WITH THERMAL INSULATION (XPS)

TECHNICAL FILE Nº 35015 - REVIEW 8/13 THIS REVIEW CANCELLS ALL PREVIOUS

COMPLETE INFORMATION OF POLITABER POL PY 30 SHEET

CE

View "Declaración de Prestaciones - DoP" in: DoP_E_32150_13707_POLITABERPOLPY30_v01

View CE Trade, complete, in: DoP_E_32150_13707_POLITABERPOLPY30_v01

ASFALTOS CHOVA, S. A.
Ctra. Tavernes a Liria, km 4,3. 46760 TAVERNES DE LA VALLDIGNA. Valencia

Sheet description:

Modified with elastomers bitumen sheet, of 3 kg/m², with nonwoven polyester felt armor, plastic outer finish. Seal by adhesion by blowtorch. In "mechanical fixed" systems to the support.

Recommended use for: base sheet in bilayer systems under heavy protection, or out in the open; monolayer in sloping roofs, under tiles with battens.

Not recommended use for: monolayer system; upper sheet in bilayer systems out in the open; upper layer in green roofs

TEST	METHOD	VALUE	UNIT	TOLERANCE	
Behaviour facing external fire:	EN 13501-5 : 2002	Broof(t1)	A. Chova documentation,		
Reaction to fire:	EN 13501-1 : 2002	Class E	verified by AENOR		
Tightness:	EN 1928 : 2000	Pass			
Traction resistance in:					
- longitudinal direction:	EN 12311-1: 1999	700	N / 5 cm	± 200	
- transversal direction:		450	N / 5 CIII	± 150	
Elongation in:					
Longitudinal direction:	EN 12311-1: 1999	35	%	± 15	
Transversal direction:		35	70	± 15	
Resistance to roots (penetration of):	EN 13948 : 2007	PND			
Static load resistance:	EN 12730 : 2001	≥ 15	kg		
Impact resistance:	EN 12691 : 2006	900	mm		
Tear resistance:	EN 12310-1: 1999				
Joints resistance: (To cutter)	EN 12317-1: 1999				
Durability:	EN 1296 : 1999				
(Plyability)	EN 1109: 1999				
(Flow resistance)	EN 1110 : 1999				
Plyability:	EN 1109: 1999	≤ -15	°C		
Dangerous substances:		PND			

Note -. For further products information, insulation or sheet, may consult the "DoP" or Technical Data Sheets of such products.